



Last Update: 13/11/2013

PA125EEV

Test	Standard	Result	Measured Unit
Density	ISO 845	125	Kg/m ³
Tensile strength	ISO 1798	1629	kPa
Elongation	ISO 1798	155.5	%
Compression 10%	ISO 844	125	kPa
Compression 25%	ISO 844	159	kPa
Compression 50%	ISO 844	268	kPa
Working Temperature Range	Internal	-60 \ 80	°C
Water Absorption %Vol (max)	Internal	1	%
Shore	ISO 868	27	A

Palfoam is a closed cell cross-linked polyethylene foam block.

Tolerances other than the above may be negotiated.

Dimensional stability 24 hr at 70C < 2%.

If holes were created during the foaming process, no more than 5 holes of diameter 2mm per 1m² sheet are acceptable.

This information on Palfoam chemically cross-linked polyethylene foam is presented to the best of our knowledge.

Data represents typical values measured on a 10 mm thick specimen and should be considered as a guideline only.

PALZIV Kibbutz Ein Hanatziv 10805 Israel. Tel: 972-4-6062999 Fax: 972-4-6062958

www.palziv.com Email: contact@palziv.com